



Heat Shrinkable Tubing Selection Guide

**SAE AS23053
(Formerly MIL-I-23053)**

MIL Spec	Type	Class	Information	RDS Number
M 23053/1	Chlorinated Polyolefin (Formerly Modified Neoprene)	1 2	-55 ^o C to + 90 ^o C -70 ^o C to +121 ^o C	R10 R10
M 23053/2	Polyvinyl Chloride PVC	1 2	Flexible Cross Linked Not Cross Linked	V H105
M 23053/3	Polyvinyl Chloride PVC	1 2	Semi-rigid Cross Linked Not Cross Linked	
M 23053/4	Dual Wall Polyolefin	1 2 3	Semi-rigid - Melt Liner Flexible – Glue Lined 2:1 Flexible – Glue Lined 3:1	W5DL O2B2 W3B2
M 23053/5	Flexible Polyolefin	1 2 3	Flame Retardant - Colors Not Flame Retardant - Clear Only Highly Flame Retardant - Colors	B2 A2 B2
M 23053/6	Semi-rigid Polyolefin	1 2	Flame Retardant - Colors Not Flame Retardant - Clear	B8 D
M 23053/7	Mylar® Polyethylene Terephthalate	1 2	Longitudinal Seam Spiral Wound	T/07
M 23053/8	Kynar® Polyvinylidene Fluoride		Semi-rigid	K
M 23053/9	Fluorosilicone		Specification Cancelled	
M 23053/10	Silicone Rubber		Flexible	T/10
M 23053/11	FEP Teflon® Fluorinated Ethylene Propylene	1 2	1.3 to 1.0 Shrink Ratio 1.67 to 1.0 Shrink Ratio	T/11 T/11
M 23053/12	TFE [PTFE] Teflon® PolyTetraFluoroEthylene	1 2 3 4 5	Heavy Wall 2:1 Shrink Ratio Standard Wall 2:1 Shrink Ratio Thin Wall 2:1 Shrink Ratio Light Wall 2:1 Shrink Ratio Fractional 4:1 Shrink Ratio	T/12 T/12 T/12 T/12 T/12
M 23053/13	Viton® Fluoroelastomer		Flexible, High temperature[200 ^o C], solvent resistant. (Clear)	FE3 KH230
M 23053/14	Tefzel® EFTE		Translucent white/Transparent blue -100 ^o C to 150 ^o C	T/14
M 23053/15	Heavy Wall Polyolefin Adhesive Lined	1 2	.155" Wall .100" Wall	T/15 T/15
M 23053/16	Elastomeric Polyolefin			R120
M 23053/17	Flame Retardant Translucent Polyolefin	1 2	Standard Wall Thin Wall	NF NF4
M 23053/18	Modified Fluoropolymer Thin Wall	1 2 3	Flexible -55 ^o C - +175 ^o C Flexible Black or White Only Extremely Flexible -55 ^o C - +150 ^o C (90 ^o Shrink Temperature)	K2 T/18 K3

Mylar, Teflon, and Tefzel are trademarks of DuPont. Kynar is a trademark of ARKEMA, Inc.
Viton is a trademark of The Chemours Company